

1/3




FIG. 1





FIG. 2

3/3

CONVENTIONAL PROCESS:
 Plain colors and prints



APPLICATION BATH:

STAINBLOCKER
 SURFACTANT
 ACID DONOR
 STAINBLOCKER A: pH 2.0-5.0
 STAINBLOCKER B: pH 6.0-7.5
 20-60°C

STEAMER

SATURATED STEAM
 60 TO 90 SECONDS

(HYDRO EXTRACTOR)


RINSE

HYDRO EXTRACTOR

DRY

CARPET TILES AND CARPETS:

Dif Dye Carpet Tiles and
 Carpets, Plain or Printed
 Carpet Tiles and Carpets.



APPLICATION BATH:

STAINBLOCKER
 SURFACTANT
 ACID DONOR
 pH 6.0-7.5
 20-95°C

28' DRYING

Infra-red dryer

32 RINSING

34 SUCTIONING

36 DRYING

FIG. 3